

2-2013

Palladium Complexes with N-Heterocyclic Carbene Ligands As Catalysts for the Alkoxy carbonylation of Olefins

Gina M. Roberts
Iowa State University

Philip J. Pierce
Iowa State University

L. Keith Woo
Iowa State University, kwoo@iastate.edu

Follow this and additional works at: http://lib.dr.iastate.edu/chem_pubs

 Part of the [Chemistry Commons](#)

The complete bibliographic information for this item can be found at http://lib.dr.iastate.edu/chem_pubs/775. For information on how to cite this item, please visit <http://lib.dr.iastate.edu/howtocite.html>.

This Article is brought to you for free and open access by the Chemistry at Iowa State University Digital Repository. It has been accepted for inclusion in Chemistry Publications by an authorized administrator of Iowa State University Digital Repository. For more information, please contact digirep@iastate.edu.

Palladium Complexes with N-Heterocyclic Carbene Ligands As Catalysts for the Alkoxy carbonylation of Olefins

Abstract

Palladium catalysts, generated from Pd(OAc)₂ and 2 equiv of *N,N*-dialkylbenzimidazolium iodide, are effective for the alkoxy carbonylation of olefins in high yields (>90%). Alkoxy carbonylation of 1-hexene in dimethylacetamide is achieved within 24 h at 110 °C using 1 mol % catalyst, 1000 psi CO, and ethanol. Reactions can be prepared in air, without the need of an acid additive to produce ethyl 2-methylhexanoate and ethyl heptanoate in approximately a 2:1 ratio.

Disciplines

Chemistry

Comments


Reprinted (adapted) with permission from *Organometallics* 32 (2013): 2033, doi:[10.1021/om300959f](https://doi.org/10.1021/om300959f).
Copyright 2013 American Chemical Society.

Palladium Complexes with N-Heterocyclic Carbene Ligands As Catalysts for the Alkoxy carbonylation of Olefins

Gina M. Roberts, Philip J. Pierce,[†] and L. Keith Woo*

Department of Chemistry, Iowa State University, Ames, Iowa 50011-3111, United States


ABSTRACT: Palladium catalysts, generated from Pd(OAc)₂ and 2 equiv of *N,N*-dialkylbenzimidazolium iodide, are effective for the alkoxy carbonylation of olefins in high yields (>90%). Alkoxy carbonylation of 1-hexene in dimethylacetamide is achieved within 24 h at 110 °C using 1 mol % catalyst, 1000 psi CO, and ethanol. Reactions can be prepared in air, without the need of an acid additive to produce ethyl 2-methylhexanoate and ethyl heptanoate in approximately a 2:1 ratio.



INTRODUCTION


Carbonylation reactions have been used to synthesize a wide variety of valuable polymer and oxygenate material.¹ Interest in Pd-phosphine catalysts for polymerization and alkoxy carbonylation of olefinic materials was piqued in the early 1980s with the discovery that cationic palladium-phosphine complexes could effectively copolymerize α -olefins with CO in the presence of methanol.^{2–6} Subsequent studies of ligand influence indicated that bidentate tertiary phosphines favored polymerization (i.e., generation of polyketones), whereas monodentate tertiary phosphines favored single-insertion alkoxy carbonylation products.^{3,7–10} While monodentate phosphines, such as triphenylphosphine, provided good yields of methyl propanoate from ethylene, longer chain olefins resulted in poor regioselectivity with mixtures of branched and linear esters.^{7,11} Improvements by the research groups of Drent,¹² Pringle,^{12,13} Tooze,^{14,15} and Cole-Hamilton¹⁶ have led to new Pd ligands (Chart 1) that greatly enhanced the linear selectivity

Chart 1. Chelating Phosphine Ligands for Alkoxy carbonylation of Olefins



for alkoxy carbonylation. Although these ligands were chelating, the enhanced steric bulk of these phosphines effectively resulted in conversion of terminal and internal C5–C14 olefins to the corresponding linear ester products (eqs 1 and 2).

In seeking to develop more robust carbonylation catalysts, we evaluated palladium *N*-heterocyclic carbene complexes. Use of NHC ligands avoids the oxygen sensitivity and multistep ligand syntheses that are often associated with the use of



phosphines.^{13,17} To date, very few Pd-NHC-catalyzed carbonylation reactions have been reported. Examples are limited to carbonylation of aryl halides, oxidative carbonylation of phenolic and amino compounds, and copolymerization of ethylene with CO.^{18–22} Herein, we report our preliminary results for the first known alkoxy carbonylation of olefins using bis(benzimidazolylidene)palladium complexes (**4a–c**). These studies illustrate the systematic differences between NHC and phosphine ligands in alkoxy carbonylation.

RESULTS AND DISCUSSION

Simple *N*-alkyl-substituted benzimidazolium salts and the corresponding palladium catalysts were readily prepared as summarized in Scheme 1. Symmetrically substituted salts **3a–c** were synthesized from benzimidazole and 1° or 2° alkyl halides by heating in CH₃CN with base.²³

Formation of the corresponding benzimidazolylidene complexes was accomplished via adapted procedures by heating Pd(OAc)₂ and the salt in a minimal amount of DMSO in air.^{24,25}

The general reaction conditions for Pd-phosphine carbonylation of olefins commonly involve (1) the use of alcohol as solvent; (2) the addition of strong Brønsted acids as activating

Received: October 12, 2012


Published: February 19, 2013



The presence of Pd was necessary, as salt **3a** alone was inactive for carbonylation in the absence of a palladium source.

Improvement of the linear selectivity by replacing the acid additive PMS with **3a** suggested that altering the acid source might be key to catalytic performance (Table 2). Initially, the influence of the pyridinium acid structure was explored. Neither the presence of a single methyl group on the pyridinium ring (2-picolinium, 2-PicMS; 4-picolinium, 4-PicMS) nor the inclusion of 2,6-methyl groups (lutidinium, LMS) resulted in a significant change in product selectivity. It was also noted that similar yield and selectivity were maintained if the mesylate anion was switched to triflate. Therefore, the range of acids was expanded to include Lewis acids (ZnCl₂, Ph₃B), nonanoic acid, and sulfonic acids (MSA; *p*-toluene sulfonic acid, PTSA), none of which provided an improvement to selectivity or yield. Surprisingly, reevaluation of the catalytic system revealed that quantitative alkoxy carbonylation could be obtained without any acid additive.

Since the optimized system was not dependent upon acid for catalysis, further evaluation of the importance of the cosolvent was undertaken. Addition of DMA was key to achieving high carbonylation yields. Yields of 8% or less occurred at 110 °C after 3 d in the absence of DMA. However, use of DMA also produced small amounts (<3%) of side products, *N,N*-dimethylheptanamide and *N,N*-dimethyl-2-methylhexanamide, which resulted from addition of DMA to hexene. To eliminate side product formation, other solvents were evaluated. Use of THF or CH₃CN as cosolvent resulted in a lower overall yield, but an improvement in linear selectivity and reduction in side products (Table 3).



Pd-NHC-catalyzed alkoxy carbonylation of additional olefins generally resulted in quantitative conversion of terminal olefins to ester product (Table 4). It is also important to note that alkoxy carbonylation of internal olefins was dramatically

Table 3. Effect of Cosolvent on Alkoxy carbonylation with Catalyst **4a^a**

entry	acid	EtOH/1-hexene	solvent	yield % (b:l)
1	PMS	1:4	DMF	trace
2	PMS	1:4	CH ₃ CN	78 (1.4)
3	none	1:4	CH ₃ CN	59 (1.4)
4	PMS	1:4	THF	27 (1.0)
5	none	1:4	THF	30 (1.1)
6	PMS	1:4	—	3 (1.0) ^b
7	none	1:4	—	8 (1.1) ^b
8	PMS	1:4	DMA	89 (1.8)
9	none	1:4	DMA	100 (1.6)
10	PMS	4:1	DMA	6 (2.1) ^c
11	MSA	4:1	DMA	7 (1.8) ^c
12	none	4:1	DMA	10 (1.8) ^c

^aConditions: 14 mmol of EtOH, 56 mmol of 1-hexene, 1 mol % **4a**, 15 mol % acid, 5 mL of DMA, 1000 psi CO, 24 h. ^bReaction ran in the absence of DMA for 72 h. ^c14 mmol of 1-hexene and 56 mmol of EtOH used.

Table 4. Alkoxy carbonylation of Various Olefins with Catalyst **4a^a**

entry	substrate	acid	yield % (b:l)
1	1-pentene	PMS	85 (1.8)
2	1-pentene		99 (1.6)
3	1-octene		100 (1.6)
4	cyclohexene	PMS	16
5	cyclohexene		83
6	ethyl 4-pentenoate		100 (2.1)
7	styrene	PMS	27 (2.2) ^b
8	ethyl acrylate	PMS	31 ^b

^aConditions: 14 mmol of EtOH, 56 mmol of olefin, 1 mol % **4a**, 15 mol % PMS, 5 mL of DMA, 1000 psi CO, 24 h. ^bLarge amount of polymer product was detected.

improved over systems that included an acid additive such as PMS. When using compounds containing a vinylic functionality (e.g., styrene and ethyl acrylate), a large amount of polymeric material was formed.

SUMMARY

We have shown that Pd benzimidazolylidene complexes are robust and high-yielding alkoxy carbonylation catalysts in the absence of acid additives. While many reports indicate analogies between phosphines and NHC ligands, it is evident from our preliminary work that Pd-NHC alkoxy carbonylation systems are quite disparate from those of Pd-phosphines. The nature of the active Pd intermediates remains unclear, but there is strong evidence that the NHC is vital to reactivity. Future studies will focus on identifying catalytic intermediates in hopes of better understanding the systematic and mechanistic differences between Pd-NHC and Pd-phosphine complexes as well as developing the scope and applicability of these catalysts in a variety of carbonylation reactions.

EXPERIMENTAL SECTION

General Considerations. All reagents and solvents were of reagent grade or higher and were used as received. 4,5-Dimethylbenzimidazole²⁷ and 1,3-diisopropylbenzimidazolium bromide²³ were synthesized following previously reported procedures. Benzimidazolium salts (**3a–c**) and the corresponding catalysts (**4a–c**) were synthesized without rigorous exclusion of air and water. The carbonylation reactions were prepared in open air prior to sealing and pressurizing the reactor. Routine NMR spectra were recorded on a Varian VXR-400 spectrometer. Gas chromatography was performed on an HP-6890 instrument fitted with a HP-5 capillary column (30 m length, 0.25 mm internal diameter, 0.25 μm film thickness).

Synthesis and Characterization of Benzimidazolium Salts **3a and **3c**.** As adapted from published reports,²³ a flask was charged with CH₃CN (10 mL), benzimidazole (8.5 mmol), and K₂CO₃ (1.18g, 8.5 mmol). MeI (4.0 equiv, 2.1 mL, 33.7 mmol) was added, and the reaction was heated at reflux for 18 h. After reaction completion, all volatiles were removed in vacuo. The residue was washed with CH₂Cl₂, and the filtrates were collected. CH₂Cl₂ was removed in vacuo, resulting in a sticky residue. Removal of the remaining benzimidazole and isolation of a solid product were achieved by sonicating the residue with EtOAc (3 × 5 mL), decanting after each sonication step. The solid was then filtered, and washed with EtOAc. The white powder was dried under vacuum for at least 24 h before use. Yield: 85–91%. NMR analysis for **3a** matched published values.²⁸ 1,3,4,5-Tetramethylbenzimidazolium iodide (**3c**): ¹H NMR (400 MHz, CDCl₃) δ 10.92 (s, 1H, NCHN), 7.43 (s, 2H, Aryl-H), 4.20 (s, 6H, NCH₃), 4.29 (s, 6H, aryl-CH₃).

Synthesis and Characterization of Benzimidazolium Salt **3b.** After dissolving 1,3-diisopropylbenzimidazolium bromide (1.0 g, 3.5

mmol) in acetone (5 mL), NaI (0.6 g, 4.0 mmol) was added. A white precipitate immediately formed, and the solution was filtered through Celite, washing with small portions of acetone. The filtrate was collected and dried in vacuo. The resulting residue was washed with dichloromethane, filtering again through Celite, and the filtrate was dried in vacuo. Removal of the remaining benzimidazole and isolation of a solid product were achieved by sonicating the residue with EtOAc (3 × 5 mL), decanting after each sonication step. The solid was then filtered, and washed with EtOAc. The white powder was dried under vacuum for at least 24 h before use. Yield: 89%. NMR analysis for **3b** matched published values.²⁵

Adapted General Synthesis of Catalysts 4a and 4c (ref 24). In a 20 mL flask, both Pd(OAc)₂ (0.5 g, 2.2 mmol) and the appropriate benzimidazolium salt (2.1 equiv, 4.7 mmol) were dissolved in a minimal amount of DMSO (5 mL). The reaction was stirred with gentle heating (30–60 °C) for 6 h. During this time the dark red-brown solution lightened to orange. The DMSO solution was filtered and washed with small amounts of DMSO, to separate any Pd black from the solution. To the DMSO filtrate was added 50 mL of H₂O to precipitate the product. The solid was collected via filtration, washed with water (3 × 50 mL), and dried under suction for 5 m. The resulting orange solid was subsequently washed with several small portions of ether and hexanes, until the filtrates were clear. The solid was dried in vacuo for at least 24 h before use. Products **4a** and **4c** were mixtures of *cis*- and *trans*-isomers, with the *trans*-isomer prevalent. The isomer mixtures were used as the carbonylation catalysts.

cis- and *trans*-**4c**: ¹H NMR (400 MHz, CDCl₃) δ 7.15 (s, 2H, Ar-H), 7.09 (s, 2H, Ar-H), 4.19 (s, 6H, NCH₃), 4.17 (2, 6H, NCH₃), 2.40 (s, 6H, Ar-CH₃), 2.35 (s, 6H, Ar-CH₃).

Adapted Synthesis of Catalyst 4b (ref 25). In a 20 mL flask, both Pd(OAc)₂ (0.5 g, 2.2 mmol) and **3b** (1.3 g, 4.6 mmol) were dissolved in a minimal amount of DMSO (5 mL). The reaction was stirred at 80 °C for 12 h, then at 100 °C until the reaction lightened to yellow-orange. To the DMSO filtrate was added 50 mL of H₂O to precipitate the product. The solid was collected via filtration, washed with water (3 × 50 mL), and dried under suction for 5 min. The resulting orange solid was subsequently washed with several small portions of ether and hexanes, until the filtrates were clear. The solid was then washed with CH₂Cl₂, collecting the filtrate. All volatiles were removed in vacuo, and the solid was dried in vacuo for at least 24 h before use. A minor amount of *cis*-**4b** was present (<5%), and excess **3b** prevented Pd-dimer formation.

General High-Pressure Reactions. To a high-pressure bomb, catalyst (0.14 mmol), acid (2.13 mmol), cosolvent (5.0 mL), olefin (55.8 mmol), and EtOH (0.83 mL, 14.2 mmol) were added in that order. The reactor was sealed and pressurized with CO to 1000 psi. The reaction was heated with stirring at the indicated temperature and pressure for the noted duration. After reaction completion, the reactor was cooled to 25 °C and depressurized. To the reaction solution were added 30 mL of hexane and 100 μL of decane, which was subsequently washed with saturated NaHCO₃ (3 × 5 mL) and saturated NaCl (3 × 5 mL). The resulting organic layer was evaluated via GC to determine product yields.

AUTHOR INFORMATION

Corresponding Author

*E-mail: kwoo@iastate.edu.

Notes

The authors declare no competing financial interest.

†ERC CBiRC REU student.

ACKNOWLEDGMENTS

We thank the NSF for partial support of this work through ERC award EEC-0813570 (the Center for Biorenewable Chemicals, CBiRC, at Iowa State University) and CHE-0809901.

REFERENCES

- (1) *Modern Carbonylation Methods*; Kollár, L., Ed.; Wiley: Weinheim, 2008.
- (2) Belov, G. P.; Novikova, E. V. *Russ. Chem. Rev.* **2004**, *73*, 267–291.
- (3) Drent, E.; Budzelaar, P. H. M. *Chem. Rev.* **1996**, *96*, 663–681.
- (4) Cavinato, G.; Toniolo, L.; Vavasori, A. In *Catalytic Carbonylation Reactions*; Beller, M., Ed.; Springer, 2006; pp 125–164.
- (5) Bianchini, C.; Meli, A. *Coord. Chem. Rev.* **2002**, *225*, 35–66.
- (6) Mul, W. P.; Oosterbeek, H.; Beitel, G. A.; Kramer, G. J.; Drent, E. *Angew. Chem., Int. Ed.* **2000**, *39*, 1848–1851.
- (7) Robertson, R. A. M.; Cole-Hamilton, D. J. *Coord. Chem. Rev.* **2002**, *225*, 67–90.
- (8) Bianchini, C.; Meli, A.; Oberhauser, W. *Dalton Trans.* **2003**, 2627–2635.
- (9) Zuidema, E.; Bo, C.; van Leeuwen, P. W. N. M. *J. Am. Chem. Soc.* **2007**, *129*, 3989–4000.
- (10) Van Leeuwen, P. W. N. M.; Zuideveld, M. A.; Swennenhuis, B. H. G.; Freixa, Z.; Kamer, P. C. J.; Goubitz, K.; Fraanje, J.; Lutz, M.; Spek, A. L. *J. Am. Chem. Soc.* **2003**, *125*, 5523–5539.
- (11) Drent, E.; Van Broekhoven, J. A. M.; Doyle, M. J. *J. Organomet. Chem.* **1991**, *417*, 235–251.
- (12) Pugh, R. L.; Drent, E.; Pringle, P. G. *Chem. Commun.* **2001**, 1476–1477.
- (13) Gee, V.; Orpen, A. G.; Phetmung, H.; Pringle, P. G.; Pugh, R. L. *Chem. Commun.* **1999**, 901–902.
- (14) Clegg, W.; Eastham, G. R.; Elsegood, M. R. J.; Tooze, R. P.; Wang, X. L.; Whiston, K. *Chem. Commun.* **1999**, 1877–1878.
- (15) Eastham, G. R.; Heaton, B. T.; Iggo, J. A.; Tooze, R. P.; Whyman, R.; Zacchini, S. *Chem. Commun.* **2000**, 609–610.
- (16) Jimenez-Rodriguez, C.; Foster, D. F.; Eastham, G. R.; Cole-Hamilton, D. J. *Chem. Commun.* **2004**, 1720–1721.
- (17) Yamamoto, Y.; Koizumi, T.; Katagiri, K.; Furuya, Y.; Danjo, H.; Imamoto, T.; Yamaguchi, K. *Org. Lett.* **2006**, *8*, 6103–6106.
- (18) Veige, A. S. *Polyhedron* **2008**, *27*, 3177–3189.
- (19) Jeletic, M.; Veige, A. In *N-Heterocyclic Carbenes in Transition Metal Catalysis and Organocatalysis*; Cazin, C. S. J., Ed.; Springer: Dordrecht, 2010; pp 217–235.
- (20) McGuinness, D. *Dalton Trans.* **2009**, *35*, 6915–6923.
- (21) Subramaniam, S. S.; Slaughter, L. M. *Dalton Trans.* **2009**, *35*, 6930.
- (22) Xue, L.; Shi, L.; Han, Y.; Xia, C.; Huynh, H. V.; Li, F. *Dalton Trans.* **2011**, *40*, 7632–7638.
- (23) Huynh, H. V.; Han, Y.; Ho, J. H. H.; Tan, G. K. *Organometallics* **2006**, *25*, 3267–3274.
- (24) Huynh, H. V.; Ho, J. H. H.; Neo, T. C.; Koh, L. L. *J. Organomet. Chem.* **2005**, *690*, 3854–3860.
- (25) Han, Y.; Huynh, H. V.; Koh, L. L. *J. Organomet. Chem.* **2007**, *692*, 3606–3613.
- (26) Clegg, W.; Eastham, G. R.; Elsegood, M. R. J.; Heaton, B. T.; Iggo, J. A.; Tooze, R. P.; Whyman, R.; Zacchini, S. *J. Chem. Soc., Dalton Trans.* **2002**, 3300–3308.
- (27) Wagner, E. C.; Millet, W. H. *Org. Synth.* **1943**, *2*, 65.
- (28) Katritzky, A. R.; Jishkariani, D.; Sakhuja, R.; Hall, C. D.; Steel, P. *J. J. Org. Chem.* **2011**, *76*, 4082–4087.