

Adhesion Hysteresis and Its Role in Vibrothermography Crack Heating

Bryan E. Schiefelbein, Tyler Lesthaeghe, Ashraf F. Bastawros, and Stephen D. Holland, Center for Nondestructive Evaluation, Iowa State University, Ames, IA 50014

Vibrothermography is an NDE inspection which uses vibration to stimulate surface cracks and measure the resultant heat generation. For years, the accepted assumption has been that heat generation in Vibrothermography NDE is due to friction between opposing crack surfaces [1–3]. A frictional mechanism suggests that crack surfaces in sliding shear would generate heat, whereas crack surfaces coming into and out of contact in an opening-closing mode would not, or would generate much less. But cracks heat easily in opening/closing mode and experimental evidence [4] is not consistent with the prediction that heat generation for shear vibration should be substantially larger than heat generation for opening-closing mode. Perhaps friction is not the dominant heating mechanism or is not the entire story. Recent experiments [5–7] have led to several observations regarding the behavior of heat generation at cracks: i) a linear dependence on excitation frequency, ii) a dependence on excitation amplitude somewhere between linear and quadratic, iii) Crack heating occurs at or near the closure point where the crack transitions from closed (crack faces in contact) to open (crack faces not in contact) We revisit the controversy over the underlying mechanism of vibrothermographic crack heating, evaluating various alternative theories, including linear absorption, irreversible thermoelasticity, friction, adhesion hysteresis, and plastic flow for consistency with the experimental evidence. We conclude only adhesion hysteresis (for opening/closing mode or sliding) and friction (for sliding mode only) are consistent with experiment.

Acknowledgement:

This material is based on work supported by the Air Force Research Laboratory under Contract #FA8650-10-D-5210, Task Order #023 and performed at Iowa State University, Case Number 88ABW-2016-2416.

References

1. Jeremy Renshaw, John C. Chen, Stephen D. Holland, and R. Bruce Thompson. The sources of heat generation in vibrothermography. *NDT & E International*, 44(8):736–739, 2011.
2. F. Mabrouki, M. Thomas, M. Genest, and A. Fahr. Frictional heating model for efficient use of vibrothermography. *NDT & E International*, 42(5):345–352, July 2009.
3. Jianping Lu, Xiaoyan Han, Golam Newaz, L. D. Favro, and R. L. Thomas. Study of the effect of crack closure in Sonic Infrared Imaging. *Nondestructive Testing and Evaluation*, 22(2-3):127–135, June 2007.
4. Wenjun Zhang. Frequency and load mode dependence of Vibrothermography. *Graduate Theses and Dissertations*, January 2010.
5. Tyler Joseph Lesthaeghe. Evaluation of some parameters influencing vibrothermographic crack heating. 2015.
6. Jeremy Renshaw, Stephen Holland, R. Thompson, and Christopher Uhl. The Effect of Crack Closure on Heat Generation on Vibrothermography. *Aerospace Engineering Conference Papers, Presentations and Posters*, July 2008.
7. Wenjun Zhang, Stephen Holland, and Jeremy Renshaw. Frequency Dependence of Vibrothermography. *Aerospace Engineering Conference Papers, Presentations and Posters*, July 2009.